Sandvik Materials Technology

Product Area Tube



www.smt.sandvik.com www.smt.sandvik.com/nafta **MATERIAL CERTIFICATE**

982 Griffin Pond Rd, Clarks Summit, PA US 18411, Ph: 570-585-7500

Cert#: 201616477

Page 1

Plant Location: 982 Griffin Pond Road, Clarks Summit, PA 18411 Ship To: Sold To: 8442 SWAGELOK MANUFACTURING COMPANY **GRANDE PRAIRIE VALVE & FITTING** GRAND PRAIRIE AB INDEPENDENCE OH Certification Date: Customer Order No: **Y13006** 20160519 Sandvik Order No: Revised Date: 20160607 310525/1 Work Order/Lot: 181597 _ _ _ _ _ _ SWAGELOK SMS-00333 Rev. D, ASTM A632-04 Cold Finished BRIGHT ANNEALED Seamless Tube Size: .125" OD X .028" AW Type TP316/TP316L (UNS S31600/S31603) Heat: 537918 ANALYSIS % Si C Mn Ρ S Cr Ni .41 .022 .027 .009 17.25 13.03 1.54 Heat .030 .011 .42 1.55 17.34 13.08 .022 Prod Cu Pb Al Mo Fe .32 .003 2.53 Heat 2.57 .32 .003 Prod Mechanical Tests: Yield Strength Tensile Elongation Reduction Of Area 0.2% 1.0% Strength in % E10" MPa E2 " E4d E5d psi MPa psi MPa psi જ N/A N/A 80910 558.0 37 N/AN/A N/A 49150 339.0 305.0 79750 550.0 38 44220 81HRBW, 81HRBW, 80HRBW, 82HRBW, 83HRBW, 83HRBW Hardness Test Results: Flare Test per ASTM A450/A1016 and ASME SA450/SA1016, No. samples: 2 Result: Acceptable Flattening Test per ASTM A450/A1016 and ASME SA450/SA1016: Acceptable Tensile Test sample width (1=Full-Size 2=1/2" Strip): 1 Country Of Origin: Germany 100% Positive Material Identification performed All material subjected to a final solution annealing heat treatment with material at a temperature of 1900 deg. F minimum followed by rapid quenching to below 800 deg. F in less than three (3) minutes. The material has not come in contact with Mercury or Mercury containing compounds. No welding has been performed on this material. Material has been eddy current tested in accordance with ASTM A450, ASTM A1016 and is acceptable. Material is capable of passing the ASTM A262 Practice "E". Inspection certificate produced in accordance with EN 10204 3.1 (formerly EN 10204 3.1.B). No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of Sandvik Materials Technology. Unauthorized alterations to the Inspection

Cert#: 201616477 Page 2

Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in EN 10204:2004, Section 6. Contravention of this notice will be prosecuted to the fullest extent of the applicable law(s). Material has been manufactured/supplied in accordance with Sandvik Materials Technology Quality Manual-Standard Products Revision 16 dated Jan. 12, 2015. Quality system has been approved to ISO 9001:2008 (Cert# GBG0000502,30AU16) No unauthorized alterations. The content of this inspection certificate may not be modified or revised in any way without the prior written approval of Sandvik Materials Unauthorized alterations to the inspection Technology. Unauthorized alterations to the inspection certifiate, including introduction of false, ficticious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. Contravention of this notice will be prosecuted to the fullest extent of the applicable laws/ This is to certify that the contents of this certificate are correct and accurate as contained in Sandvik's records, and that all above test results and operations performed are in compliance with the requirements of the purchase order and the specification(s) listed above.

John Scherer, Quality Mgr-Tube Authorized Representative 10 (SWINST1/8-316 R16) (10) CF (YH7118)